

Panasonic Electric Works Electronic Materials Europe GmbH

Specification Sheet

Specification sheet #	IPC-4101B/21	2: N/A
Reinforcement	1: Woven E-Glass	
Resin System:	Primary: Difunctional Epoxy	
	Secondary 1: Multifunctional Epoxy	Secondary 2: N/A
Flam retardant mechanism	Bromine	Minimum UL94 Requirement: V0
Fillers:	N/A	
ID Reverence:	UL/ANSI: FR-4	Mil-S-13949: /04-GF,GFN,GFK,GFP,GFM
	ANSI: FR4 / 21	
Glass transition (TG):	110°C -150°C	

Product name	Laminate: MC-100MS/EX	Prepreg: MC-Rheopreg
UL - Designation	MC-100MS/MC-100EX	MC-Rheopreg

1. Laminate		IPC Specification < 0, 5mm	IPC Specification ≥ 0, 5mm	Units	Typical Values < 0, 5mm	Typical Values ≥ 0, 5mm	Methode IPC-TM-650 (or as noted)
Physical Property							
Peel strength, minimum							
A: Low profile and very low profile copper foil, all copper foils > 18µm	18µm	0,7	0,7	N/mm	0,9	0,9	2.4.8 2.4.8.2 2.4.8.3
B: Standard profile copper foil	35µm	-	-		-	-	
1. after thermal stress		0,8	1,05		1,8	1,9	
2. at 125°C		0,7	0,7		1,7	1,8	
3. after process solutions		0,55	0,8		1,8	1,9	
Moisture Absorptions, maximum		-	0,8	%	-	0,11	2.6.2.1
Flexural strength, minimum	A: Length direction	-	415	N/mm ²	-	580	2.4.4
	B: Cross direction	-	345		-	410	
Flammability (Laminate and prepreg as laminated)		V0 min	V0 min	Rating	V0	V0	UL 94
CTE (pre / post Tg)							
Z		-	-	ppm/°C	-	65/290	2.4.24
X		-	-		-	13	
Y		-	-		-	15	
T260 (TMA)	copper removed	-	-	minutes	-	15	2.4.24.1
T288 / T300 (TMA)	copper removed	-	-	minutes	-	1 / -	2.4.24.1
Density		-	-	g/cm ³	1,91	1,91	
Decomposition Temperature		-	-	°C	-	310	TGA
Electrical Property							
Volume resistivity, minimum	A: 96 / 35 / 90	1,0 E+06	-	MΩm-cm	1,9 E+08	-	2.5.17.1
	B: after moisture resistance	-	1,0 E+06		-	8,6 E+08	
	C: at elevated temp. E-24/125	1,0 E+03	1,0 E+03		2,5 E+07	3,1 E+07	
Surface resistivity, minimum	A: 96 / 35 / 90	1,0 E+04	-	MΩm	3,8 E+07	-	2.5.17.1
	B: after moisture resistance	-	1,0 E+04		-	6,9 E+06	
	C: at elevated temp. E-24/125	1,0 E+03	1,0 E+03		8,6 E+06	4,8 E+06	
Dielectric breakdown, minimum		-	40	kV	-	> 50	2.5.6
Permittivity, maximum (laminate and prepreg as laminated)	at 1 MHz	5,4	5,4	-	N/A	4,77	2.5.5.2/3/9
	at 1 GHz	-	-	-	N/A	4,32	
Loss tangent, maximum (laminate and prepreg as laminated)	at 1 MHz	0,035	0,035	-	0,018	0,018	2.5.5.2/3/9
	at 1 GHz	-	-	-	0,018	0,018	
Arc resistance, minimum		60	60	sec	NI	NI	2.5.1
Electrical strength, minimum (laminated and prepreg as laminated)		30	-	kV/mm	56	-	2.5.6.2
CTI (comparative tracking index)		-	-	V	-	200	IEC 112
Thermal Property							
Thermal stress 10 sec at 288°C, minimum	A: unetched	Pass	Pass	Rating	Pass	Pass	2.4.13.1
	B: etched	Pass	Pass		Pass	Pass	
Tg by DSC (TMA / DMA)		110min	110min	°C	134,8	137(138/147)	2.4.25
Thermal conductivity		-	-	W/mK	-	0,38	Laser flash
Specific heat		-	-	J/kgK	-	920	DSC
2. Prepreg Property		IPC-Specification		Units	Typical Values		
Shelf life, minimum (from date of delivery)	A: Condition <20°C, rel. H. <50%	90		Days	meets requirements		AABUS
	B: Condition < 5°C	180			meets requirements		
Volatile content, maximum		0,75		%	< 0,3		2.3.19
Prepreg parameters		-	-	-	AABUS		AABUS

AABUS= As agreed between user and supplier

Note:

Text data contained in this data sheet represents typical values and does not constitute any warranty or guarantee. For review of critical specification tolerances, please contact a Panasonic Electric Works representative. Panasonic Electric Works reserve the right to change these typical values as a natural process of referring our test equipment and technics.